

# Revealing the ligand-hole localization behaviors in oxides with unusual high-valence Fe

June 18 2012




Fig. 1: Crystal structures of the simple perovskite ABO<sub>3</sub> (left) and the A-site-ordered double-perovskite AA'B<sub>4</sub>O<sub>12</sub> (right).

Japanese researchers revealed the mechanism of the functional properties of oxides with unusual valence Fe. The paper was published in a Nature publishing group journal [Scientific Reports](#).

Iron ions in oxides usually show the +2 and +3 oxidation states typically seen in wüstite (Fe<sup>2+</sup>O), magnetite (Fe<sup>2+</sup>Fe<sup>3+</sup>2O<sub>4</sub>), and hematite (Fe<sup>3+</sup><sub>2</sub>O<sub>3</sub>). A few oxides, such as SrFeO<sub>3</sub> and CaFeO<sub>3</sub>, contain unusual high-oxidation-state iron ions like Fe<sup>4+</sup>, and the behaviors of such high-valence iron ions have been attracting much attention for a long time.

The research team recently discovered new such compounds; CaCu<sub>3</sub>Fe<sub>4</sub>O<sub>12</sub> and LaCu<sub>3</sub>Fe<sub>4</sub>O<sub>12</sub> with the A-site-ordered perovskite

structure (see Fig. 1). The compounds contain iron ions with unusual valence states and exhibit distinct electronic behaviors at low temperatures, *e.g.* charge disproportionation ( $4\text{Fe}^{4+} \rightarrow 2\text{Fe}^{3+} + 2\text{Fe}^{5+}$ ) in  $\text{CaCu}_3\text{Fe}_4\text{O}_{12}$  and intersite charge transfer ( $3\text{Cu}^{2+} + 4\text{Fe}^{3.75+} \rightarrow 3\text{Cu}^{3+} + 4\text{Fe}^{3+}$ ) in  $\text{LaCu}_3\text{Fe}_4\text{O}_{12}$ . In the present study, they made solid solutions of  $\text{CaCu}_3\text{Fe}_4\text{O}_{12}$  and  $\text{LaCu}_3\text{Fe}_4\text{O}_{12}$  and investigated their temperature-dependent transitions. Although the charge-disproportionation and intersite-charge-transfer behaviors look completely different from each other in simple ionic models, they can both be explained by the localization of ligand holes, which are produced by the strong hybridization of iron *d* and oxygen *p* orbitals in oxides. In the charge-disproportionated phase the ligand holes are localized at the Fe site and the transition is regarded as one to the rock-salt-type charge ordering of the ligand holes. In the intersite charge transfer, on the other hand, the ligand holes are localized at the Cu site and the transition can be regarded as a Mott transition of the ligand holes. *TCT* decreases with increasing concentration of the ligand-hole carriers (see Fig. 2).




Fig. 2: Compositional phase diagram for the  $\text{Ca}_{1-x}\text{La}_x\text{Cu}_3\text{Fe}_4\text{O}_{12}$  solid

solution and the ligand-hole localization model of charge disproportionation and intersite charge-transfer transition behaviors.

In the A-site-ordered perovskite-structure [oxides](#), transition metals at both A' and B sites mediate A'-A', A'-B, and B-B interactions that lead to intriguing physical properties. The ligand holes produced by the strong hybridization of transition-metal cation d orbitals and oxygen p orbitals also play important roles in giving rise to various electronic and structural properties. The present A-site-ordered perovskite-structure  $\text{Ca}_{1-x}\text{La}_x\text{Cu}_3\text{Fe}_4\text{O}_{12}$  solid solution is a novel example exhibiting interplay of the interactions mediated by the ligand holes.

**More information:** Wei-Tin Chen, et al. Ligand-hole localization in oxides with unusual valence Fe. *Scientific Reports* 2, Article number: 449, 2012/06/11/online, [doi: 10.1038/srep00449](https://doi.org/10.1038/srep00449)

Provided by Kyoto University

Citation: Revealing the ligand-hole localization behaviors in oxides with unusual high-valence Fe (2012, June 18) retrieved 10 April 2024 from <https://phys.org/news/2012-06-revealing-ligand-hole-localization-behaviors-oxides.html>

This document is subject to copyright. Apart from any fair dealing for the purpose of private study or research, no part may be reproduced without the written permission. The content is provided for information purposes only.