


'Sandwich' structure key to thin LSMO films retaining magnetic properties

June 11 2019, by Tracey Peake



Atomic-scale structure obtained by high-resolution electron microscopy. Credit: NC State University

Researchers at North Carolina State University have found that the oxide ceramic material lanthanum strontium manganite (LSMO) retains its magnetic properties in atomically thin layers if it is "sandwiched" between two layers of a different ceramic oxide, lanthanum strontium chromium oxide (LSCO). The findings have implications for future use

of LSMO in spintronic-based computing and storage devices.

In its bulk form LSMO has both magnetic and metallic properties. The conductivity of the material can be altered by changing its [magnetic field](#), which makes LSMO appealing for use as a switch in spintronic devices. However, when the material gets to a certain thinness—between five and 10 atomic layers—it loses these properties.

Divine Kumah, assistant professor of physics at NC State and corresponding author of a paper describing the work, wanted to know why LSMO loses its magnetic properties at a particular thinness, and to find a way to make LSMO magnetic in thin form.

Kumah, with colleagues and graduate students from NC State, first grew thin films of LSMO on strontium titanate—a non-magnetic substrate commonly used as a neutral scaffold. The team grew films ranging from two to 10 atomic layers thick and tested them for magnetic properties.

Next, the team utilized the synchrotron light source at Argonne National Laboratory so that they could get a three-dimensional view of the arrangement of the [atoms](#) within the thin layers of LSMO. They found that at extreme thinness, the oxygen and manganese atoms moved slightly out of alignment on the surface of the material, effectively switching off its magnetism.

"At about five atomic layers we saw distortions on the surface of the [layer](#) and at the bottom interface with the scaffold," Kumah says. "The oxygen and manganese atoms rearrange themselves. Magnetism and [electrical conductivity](#) in LSMO are related to how these two atoms bond, so if there are polar distortions in the film where they move up and down, the bonds stretch out, electrons can't move through the material effectively and magnetism is switched off."

The team noted that these distortions started at the top of the film and extended approximately three layers below surface.

"We found that the distortions occur because the [crystal structure](#) creates an [electric field](#) at the surface," Kumah says. "The oxygen and manganese atoms move in order to cancel the electric field. Our challenge was to grow something at the interfaces that is compatible with LSMO structurally but that is also insulating—so that we remove the electric field, stop the movement of the oxygen and manganese atoms and retain magnetic properties."

The researchers found that by using two layers of LSCO on either side of the LSMO, the LSMO could retain its [magnetic properties](#) at two atomic layers.

"It is like a sandwich—LSCO is the bread and LSMO is the meat," Kumah says. "You can use fewer than five layers of LSMO in this arrangement without any atomic displacement. Hopefully our work has shown that these [materials](#) can be thin enough to be useful in spintronics devices."

More information: Sanaz Koohfar et al, Confinement of magnetism in atomically thin $\text{La}_{0.7}\text{Sr}_{0.3}\text{CrO}_3/\text{La}_{0.7}\text{Sr}_{0.3}\text{MnO}_3$ heterostructures, *npj Quantum Materials* (2019). [DOI: 10.1038/s41535-019-0164-1](https://doi.org/10.1038/s41535-019-0164-1)

Provided by North Carolina State University

Citation: 'Sandwich' structure key to thin LSMO films retaining magnetic properties (2019, June 11) retrieved 10 April 2024 from <https://phys.org/news/2019-06-sandwich-key-thin-lsmo-retaining.html>

This document is subject to copyright. Apart from any fair dealing for the purpose of private study or research, no part may be reproduced without the written permission. The content is provided for information purposes only.