

Breakthrough in electrocatalysts reported

September 26 2019, by Huang Weijian




Fig. 1. Structural characterizations of PdMo bimetallic nanosheets. a–c, Low-magnification HAADF-STEM (a), high-magnification HAADF-STEM (b) and TEM (c) images of PdMo bimetallic nanosheets. The inset of c shows an HRTEM image of PdMo bimetallic nanosheets. d, e, AFM image (d) and corresponding height profiles (e) of PdMo bimetallic nanosheets. f, High-resolution HAADF-STEM image taken from a single bimetallic nanosheet. Inset, the corresponding fast Fourier transform patterns. Credit: Peking University

Recently, the group of Professor Guo Shaojun in College of Engineering at Peking University developed a novel type of sub-nanometer, highly curved PdMo nanosheet—due to its structural analogy with graphene, it was denoted as PdMo bimetalene, and showed extraordinary electrocatalytic performance toward the oxygen reduction reaction (ORR) in alkaline environment. When used as the cathode electrocatalysts, the PdMo nanosheets enable much enhanced charging/discharging performance in Zn-air and Li-air batteries. This work was published in *Nature* on September 26th, 2019.

Fossil fuels have caused severe challenges in environmental pollution and [climate change](#), thus urgently calling for the development of renewable clean energy technologies that enable a sustainable energy system. The storage and subsequent use of renewable yet intermittent energy sources, e.g., solar, wind etc., requires an electrochemical device that enables the interconversion of electricity and chemicals in an efficient manner. Of key importance to the operational efficiency of the device lies on the electrode-electrolyte interface, in which the desired electrochemical reactions occur as driven by a suitable electrocatalyst. Currently, the lack of high-performing electrocatalyst creates a bottleneck to the penetration of renewable energy.

One of the biggest challenges in this field is the unfavorable kinetics of the ORR, and platinum group metals (PGMs)-based electrocatalysts are often required to improve the activity and durability. In the past decade, the ORR dynamics in acidic environments on platinum-based catalysts have been drastically improved via the tuning of alloying, surface strain, and optimized coordination environments. Nevertheless, improving the activity of this reaction in alkaline media remains challenging due to the difficulty in achieving optimized oxygen binding strength on PGMs in the presence of hydroxide.

In this study, PdMo bimetalene has been demonstrated to be an efficient

and stable electrocatalyst for the ORR and the OER in alkaline electrolytes, and promising cathodic electrodes in Zn–air and Li–air batteries. The ultrathin feature of PdMo bimetallic enables an impressive electrochemically active surface area ($138.7 \text{ m}^2/\text{gPd}$) and a mass activity toward the ORR of 16.37 A/mgPd at 0.9 volts versus RHE in alkaline electrolytes. This mass activity is 78 times and 327 times higher than that of commercial Pt/C and Pd/C catalysts, respectively, along with negligible decay after 30,000 accelerated cycling. Density functional theory calculations show that an optimized oxygen binding energy was achieved on PdMo bimetallic due to a combination of alloying effect, strain effect and the quantum size effect. It is envisioned that the metallic materials will show great promise in energy electrocatalysis.




Fig. 2. Electrocatalytic performance and mechanism study. a, b, ORR polarization curves (a) and a comparison of the mass- and specific activities (b) of the stated catalysts in 0.1 M KOH at 0.9 V versus RHE. c, Left, side view of the atomic model of the four-layer PdMo bimetallic. Right, top view of the atomic model showing layers 2 and 3. In layers 2 and 3, each molybdenum atom is surrounded by six palladium atoms, indicated by the red (layer 2) and blue (layer 3) hexagons. d, Oxygen binding energy (ΔE_O) of PdMo bimetallic as a function of compressive (negative) and tensile (positive) strains. The horizontal red line indicates the optimal ΔE_O value. e, The projected electronic density of

states of the d-band for the surface palladium atoms in bulk Pd, a four-layer Pd sheet (Pd 4L) and PdMo. The horizontal dashed lines indicate the calculated d-band centre. Credit: Peking University

More information: Mingchuan Luo et al. PdMo bimetallic for oxygen reduction catalysis, *Nature* (2019). [DOI: 10.1038/s41586-019-1603-7](https://doi.org/10.1038/s41586-019-1603-7)

Provided by Peking University

Citation: Breakthrough in electrocatalysts reported (2019, September 26) retrieved 24 April 2024 from <https://phys.org/news/2019-09-breakthrough-electrocatalysts.html>

This document is subject to copyright. Apart from any fair dealing for the purpose of private study or research, no part may be reproduced without the written permission. The content is provided for information purposes only.