

## Simpler graphene method paves way for new era of nanoelectronics

March 15 2022



"Our observation will indeed increase the scope of such flexible graphene films in this field. This could also usher the new era of flexible electronics", says Munis Khan. Credit: Chalmers University of Technology

Ever since its discovery in 2004, graphene has received attention owing to its extraordinary properties, among them its extremely high carrier mobility. However, the high carrier mobility has only been observed using techniques that require complex and expensive fabrication methods. Now, researchers at Chalmers report on a surprisingly high charge-carrier mobility of graphene using much cheaper and simpler



methods.

"This finding shows that graphene transferred to cheap and flexible substrates can still have an uncompromisingly high mobility, and it paves the way for a new era of graphene nano-electronics," says Munis Khan, researcher at Chalmers University of Technology.

Graphene is the one-atom-thick layer of carbon atoms, known as the world's thinnest material. The material has become a popular choice in semiconductor, automotive and optoelectronic industry due to its excellent electrical, chemical, and material properties. One such property is its extremely <u>high carrier mobility</u>.

"In solid-state physics, the electron <u>carrier</u> mobility characterizes how quickly an electron can move through a metal or semiconductor when pulled by an <u>electric field</u>. The high electron mobility of graphene points to great potential for broadband communications and high-speed electronics operating at terahertz switching rates. In addition, the other <u>material properties</u>, such as high chemical stability, excellent transparency, and electrical sensitivity towards biochemicals, make it a promising material for displays, light harvesting devices and biosensors," says Munis Khan.

However, the extremely high carrier mobility in graphene is either observed in mechanically exfoliated graphene, a process that lacks industrial scalability, or graphene devices fabricated on hexagonal-boron nitride. Such high mobilities have also been observed by transferring graphene grown by a process called <u>chemical vapor deposition</u> (CVD) to complex-oxide heterostructures. All these techniques require complex and expensive fabrication methods, which not only makes it more expensive but also hinder mass production of such devices.

## **Cheaper graphene with high carrier mobility**



Now, Munis Khan and his colleagues report on a surprisingly high charge-carrier mobility of CVD graphene grown on unpolished copper foil and transferred to EVA/PET lamination foil by using an ordinary office laminator and wet etching of copper. The mobility increased up to eight times after simply holding the graphene-on-plastic sandwich at 60 C for a few hours.

"This finding shows that even cheap and flexible graphene devices can still have an uncompromisingly <u>high mobility</u>," says Munis Khan. "Our article proposes a straightforward method to fabricate cheap graphene devices on flexible substrates with high carrier mobility, probably only limited by the CVD process and purity of copper."

CVD graphene transferred to EVA/PET is being intensely explored and studied for flexible and stretchable electronics, especially in shapeconforming systems such as portable energy-harvesting devices, electronic skin, and wearable electronic devices, which need high flexibility and stretchability. Conventional semiconductors lack the superior mechanical properties that graphene possesses, which makes them unsuitable for such applications—often highly conductive flexible graphene films possessing high carrier mobility are required.

"Our observation will indeed increase the scope of such flexible graphene films in this field. This could also usher the new era of flexible electronics. Applications requiring highly conductive thin films can now be realized by an affordable and simple method as proposed in our article. Indeed, in our research group we intend to use such graphene films for making extremely sensitive biosensors, terahertz detectors and high frequency devices, applications that too requires high carrier mobility. The challenge will be to integrate microfabrication techniques to make devices on <u>flexible substrates</u>. Once such issues are addressed, probably within 2-3 years, we can start utilizing such graphene films to fabricate devices for industrial use," says Munis Khan.



## About the discovery

Chemical vapor deposition (CVD) of graphene on commercial copper (Cu) foils provides a scalable route towards high-quality single-layer graphene. The CVD method is based on gaseous reactants that are deposited on a substrate. The graphene is grown on a metallic surface like Cu, Pt or Ir, after which it can be separated from the metal and transferred to specifically required substrates. The process can be simply explained as carbon-bearing gasses that react at high temperatures (900–1100 degrees Celsius) in the presence of a metal catalyst, which serves both as a catalyst for the decomposition of the carbon species and as a surface for the nucleation of the graphene lattice.

The researchers have discovered that CVD graphene once transferred from copper to EVA/PET (ordinary lamination pouch) by hot press lamination, initially showed low carrier mobility in a range from  $500-1000 \text{ cm}^2/(\text{V s})$ . But, once such films were kept at 60 C for several hours in a constant flow of nitrogen, the mobility increased eight times and reached  $6000-8000 \text{ cm}^2/(\text{V s})$  at room temperature.

The research was published in Nanomaterials.

**More information:** Munis Khan et al, High Mobility Graphene on EVA/PET, *Nanomaterials* (2022). DOI: 10.3390/nano12030331

## Provided by Chalmers University of Technology

Citation: Simpler graphene method paves way for new era of nanoelectronics (2022, March 15) retrieved 16 June 2024 from <u>https://phys.org/news/2022-03-simpler-graphene-method-paves-era.html</u>



This document is subject to copyright. Apart from any fair dealing for the purpose of private study or research, no part may be reproduced without the written permission. The content is provided for information purposes only.