


Beyond van der Waals: The next generation of covalent 2D-2D heterostructures

April 28 2022, by Elena Alonso-Redondo



2D MoS₂ is connected to graphene using a covalent bond. Credit: Patricia Bondia

A team of scientists have "velcroed" 2D structures of MoS₂ and graphene using a covalent connection for the first time. The 2D-2D structures were used to build robust field effect transistors with controlled electronic communication, interface chemical nature and interlayer distance.

The most widespread method for the synthesis of 2D-2D heterostructures is the direct growth of materials on top of each other. 2D structures are atomically thin layered materials that can be stacked to build functional heterostructures. In such structures built by atomic deposition, 2D layers are weakly bonded by van der Waals interactions and can be taken apart in some solvents or thermal processes. The lack of control over the interface of the two materials in terms of [electronic communication](#), chemical nature or interlayer distance thus impedes the construction of robust multi-purpose devices.

A team of researchers at Universidad Autónoma de Madrid and IMDEA Nanociencia (Spain) have connected covalently for the first time layers of 2D materials: MoS₂ and [graphene](#). The team has used the tools of synthetic chemistry to "sew" several flakes of MoS₂ to single-layer graphene devices, using a bifunctional molecule with two anchor points. The results, published now in *Nature Chemistry*, show that the final electronic properties of the heterostructure are dominated by the molecular interface.

The combination of the semiconducting properties of transition metal dichalcogenide MoS₂ with the high carrier mobility of graphene is particularly attractive for multiple applications. The group built [field-effect transistors](#) to test the electrical properties of the structure. They found a modification in the gate-voltage characteristic, with a shift of the Dirac cone towards positive voltages and a reduction of the current at

the minimum.

This current suppression in graphene is unambiguously associated to the disruption of the sp^2 hybridization into sp^3 due to the formation of covalent bonds. A control experiment with pristine MoS_2 suspended on top of graphene showed no significant changes in the D band intensity. Interestingly, the charge carrier mobility is conserved after functionalization and covalent bond formation between MoS_2 and graphene, being the degree of graphene doping controllable via the degree of functionalization.

The fabrication of these 2D-2D covalent heterostructures is relatively easy. A silicon substrate containing a single-layer graphene sheet was immersed in a suspension of functionalized MoS_2 in water at 35 °C. Two hours of functionalization were enough to promote the [covalent bonding](#) in most of the graphene spots. To confirm the covalent functionalization, Raman spectroscopy was performed to track the transformation of sp^2 carbon atoms of the graphene to sp^3 as indication of formation of a new C-C bond.

For the first time, researchers have used the tools of chemistry to covalently bond 2D materials. The results show the power of the chemical approach to build MoS_2 -graphene heterostructures beyond van der Waals preserving the carrier mobility of graphene for high performance FET devices. The vertical covalent connection brings an additional lever to the final properties of nanodevices beyond the intrinsic properties of the materials, and has the potential for facile high-throughput homologation.

More information: Manuel Vázquez Sulleiro et al, Fabrication of devices featuring covalently linked MoS_2 -graphene heterostructures, *Nature Chemistry* (2022). [DOI: 10.1038/s41557-022-00924-1](https://doi.org/10.1038/s41557-022-00924-1)

Provided by IMDEA Nanociencia

Citation: Beyond van der Waals: The next generation of covalent 2D-2D heterostructures (2022, April 28) retrieved 22 June 2024 from <https://phys.org/news/2022-04-van-der-waals-covalent-2d-2d.html>

This document is subject to copyright. Apart from any fair dealing for the purpose of private study or research, no part may be reproduced without the written permission. The content is provided for information purposes only.