

A novel interfacial regulated broadband photocatalyst

December 7 2022



a) Schematic illustration for the fabrication of NYF@DCN. SEM images of b)



precursor and c) DCN. TEM images of d) DCN, e) NYF, and f, g) NYF@DCN. h) Elemental mapping of NYF@DCN (scale bar: 500 nm). Credit: Science China Press

Extending the light absorption from ultraviolet (UV) to near-infrared (NIR) region and improving photocarrier separation efficiency of photocatalysts are of vital importance for solar-driven H_2 evolution.

Recently, Prof. Gouxiu Wang's research group from University of Technology Sydney jointly with Prof. Dan Wang from Chinese Academy of Sciences (Institute of Process Engineering) reported a novel interfacial regulated broadband photocatalyst composed of defective $g-C_3N_4$ (DCN) and NaYF₄: Yb³⁺, Tm³⁺ (NYF) nanocrystals in *National Science Open*.

Dr. Xiaochun Gao (University of Technology Sydney; Ludong University) and Prof. Nailiang Yang (Institute of Process Engineering, Chinese Academy of Sciences) are the co-first authors.

The authors firstly realized a precise defect control on $g-C_3N_4$ by introducing the S dopants and C vacancies into the 3-D DCN hexagonal prisms. Afterwards, the NYF nanocrystals were successfully loaded onto DCN matrix, forming the broadband NYF@DCN photocatalyst.

Precise interfacial control on DCN with optimized defect states

The authors found that the use of ethylene glycol and molten sulfur is critical to regulate the defect states in DCN via the creation of S dopants and C vacancies.



The defect states can not only extend the solar absorption ability of DCN but also accommodate the <u>excited electrons</u> from valance band and migrated electrons from conductive band via a moderate electrontrapping ability, further improving the charge separation efficiency in the interface between DCN and solution.

Extended solar harvesting of NYF@DCN

In comparison with bulk g- C_3N_4 (BCN) and DCN, the broadband NYF@DCN exhibited an enhanced solar light harvesting ability, which was mainly due to:

1) The formation of defect states in DCN which lowers the excitation energy and extends the visible absorption range to 590 nm, giving a high photocurrent of 12.55 μ A cm⁻² under 550 nm;

2) The secondary excitation of DCN by the upconverted UV light from NYF crystals as reflected by the upconversion photoluminescence spectra, which rendered NYF@DCN with a promoted photocurrent of $8.01 \ \mu A \ cm^{-2}$.

The above mentioned enhanced solar absorption is inferred to boost the solar driven H_2 evolution.

Accelerated interfacial charge transfer of NYF@DCN

The CP-MAS ¹³N NMR spectra and theoretical calculations showed that, in comparison with BCN, a stronger interfacial charge polarization might exist via the Y-N bonding between DCN and NYF, which is favorable for the energy transfer from NYF to DCN via both the photo transfer (PT) pathway and excited state <u>energy transfer</u> (ET) pathway.



In summary, the enhanced solar harvesting ability and interfacial charge transfer jointly boost the broadband NYF@DCN with a superior solar driven H₂ evolution rate of 2799 μ mol h⁻¹ g⁻¹, ranking the top among the g-C₃N₄ based photocatalysts and upconversion particles-based photocatalysts.

More information: Xiaochun Gao et al, Defect and Interface Control on Graphitic Carbon Nitrides/Upconversion Nanocrystals for Enhanced Solar Hydrogen Production, *National Science Open* (2022). <u>DOI:</u> <u>10.1360/nso/20220037</u>

Provided by Science China Press

Citation: A novel interfacial regulated broadband photocatalyst (2022, December 7) retrieved 30 June 2024 from <u>https://phys.org/news/2022-12-interfacial-broadband-photocatalyst.html</u>

This document is subject to copyright. Apart from any fair dealing for the purpose of private study or research, no part may be reproduced without the written permission. The content is provided for information purposes only.