


New method stabilizes rhombohedral sodium manganese hexacyanoferrates for high-energy Na-ion batteries

February 21 2023, by Li Yuan



The sodium manganese hexacyanoferrate full-cell configurations show comparable energy density to that of the well-known LiFePO₄ full cells. Credit: *Angewandte Chemie International Edition* (2023). DOI: 10.1002/anie.202217761

The rhombohedral sodium manganese hexacyanoferrates (MnHCF) is

regarded as a scalable, low-cost, and high-energy cathode material for Na-ion batteries due to the absence of crystal water.

However, the unexpected Jahn-teller effect and significant phase transformation causes Mn dissolution and anisotropic volume change, leading to capacity loss and structural instability. Thus, it is important to build a robust and full coverage coating on the surface of MnHCF particles to address the cycling instability.

A research group led by Prof. Zhao Junmei from the Institute of Process Engineering (IPE) of the Chinese Academy of Sciences reported a simple room-temperature route to construct a magical Co_xB skin on the surface of MnHCF, demonstrating thousands-cycle level cycling lifespan and high energy density close to LiFePO_4 for Li-ion batteries.

The study was published in *Angewandte Chemie International Edition* on Jan. 31.

"Room-temperature-synthesized Co_xB seems to be tailor-made as a coating substance of MnHCF cathode," said Prof. Zhao. "Meanwhile, Co_xB is a metallic borate glass, and due to high corrosion- and wear-resistance, it shows good mechanical flexibility, which is expected to prevent the fracture or fragmentation of cathode particles."

Moreover, Co_xB can work as a double conductor of mixed electrons and ions. These unique advantages make the optimal Co_xB -coated MnHCF cathode (MnHCF-5% Co_xB) deliver an initial capacity of $\sim 133 \text{ mA h g}^{-1}$ at 10 degrees C, higher than that of bare MnHCF ($\sim 110 \text{ mA h g}^{-1}$).

More importantly, the coated samples can remain a capacity retention of over 80%, far superior to that of the pristine one (41%). In the full-cell configurations, the MnHCF-5% Co_xB //HC delivers a high energy density of 310 Wh kg^{-1} based on the total mass of cathode/anode active

substances, which is comparable to the commercial LFP [cathode](#) ($\sim 330 \text{ Wh kg}^{-1}$).

"MnHCF-5%Co_xB//HC shows an impressive capacity retention of $\sim 71\%$ at 5 degrees C after cycling 1,000 cycles, which is a significant breakthrough among the nonaqueous MnHCF full cells," said Prof. Zhao.

More information: Chunliu Xu et al, Surface Engineering Stabilizes Rhombohedral Sodium Manganese Hexacyanoferrates for High-Energy Na-Ion Batteries, *Angewandte Chemie International Edition* (2023). [DOI: 10.1002/anie.202217761](https://doi.org/10.1002/anie.202217761)

Provided by Chinese Academy of Sciences

Citation: New method stabilizes rhombohedral sodium manganese hexacyanoferrates for high-energy Na-ion batteries (2023, February 21) retrieved 15 May 2024 from <https://phys.org/news/2023-02-method-stabilizes-rhombohedral-sodium-manganese.html>

<p>This document is subject to copyright. Apart from any fair dealing for the purpose of private study or research, no part may be reproduced without the written permission. The content is provided for information purposes only.</p>
--