

# Solar cells will be fabricated by a single organic semiconductor

29 March 2011, By Mikiko Tanifuji

The fabrication of organic thin-film solar cells has been simplified due to new research findings. Where previously two types of organic semiconductors were required, doping the semiconductor fullerene with molybdenum oxide renders the use of phthalocyanine unnecessary.

The Institute for Molecular Science, National Institute of Natural Sciences announced on March 3, 2011 that a research group led by Professor Masahiro Hiramoto has succeeded in converting conduction-type of [fullerene](#) from n- to p-type by molybdenum oxide ( $\text{MoO}_3$ ) doping. Details are published online in *Applied Physics Letters* on February 28, 2011.

Although organic thin-film solar cells are promising devices because of the advantages of being light weight, flexible and low cost, the conduction-type of organic semiconductors has not been controlled by doping [impurities](#) as is done in silicon. Two species of organic semiconductors, n-type fullerene ( $\text{C}_{60}$ ) and p-type phthalocyanine (Pc), need to be used to form built-in fields in solar cells.

Researchers noticed that  $\text{MoO}_3$  is used to raise holes in organic electroluminescent materials. They have succeeded in converting conduction-type of  $\text{C}_{60}$  from n- to p-type by co-evaporation of  $\text{MoO}_3$  and  $\text{C}_{60}$ . Energetic value of the Fermi level, 4.60eV, for nondoped  $\text{C}_{60}$  films measured by the Kelvin vibrating [capacitor](#) method was positively shifted to 5.88 eV by the co-evaporated doping of  $\text{MoO}_3$  at a concentration of 3300 ppm and approached the valence band of located at 6.4 eV. The upward bending of energy band in the Schottky junction formed at the interface between a metal (silver, Ag) and p-type  $\text{C}_{60}$  film formed by  $\text{MoO}_3$  doping was confirmed based on the photovoltaic properties. [Organic solar cells](#) could be fabricated by a single material - fullerene  $\text{C}_{60}$ .

to p-type by molybdenum oxide doping", *Applied Physics Letters* Vol.98, No. 7, p. 073311 (2011); [doi:10.1063/1.3556312](https://doi.org/10.1063/1.3556312) (3 pages); published online 18 February 2011.

Provided by National Institute for Materials Science

**More information:** Masayuki Kubo, et al.  
"Conduction-type control of fullerene films from n-

APA citation: Solar cells will be fabricated by a single organic semiconductor (2011, March 29) retrieved 18 September 2019 from <https://phys.org/news/2011-03-solar-cells-fabricated-semiconductor.html>

*This document is subject to copyright. Apart from any fair dealing for the purpose of private study or research, no part may be reproduced without the written permission. The content is provided for information purposes only.*