


Mn-doped ZnS is unsuitable to act as a dilute magnetic semiconductor

February 20 2012



This shows (a) Room temperature ESR spectra of ZnS:Mn; and (b) Low temperature ESR spectra of ZnS:Mn (20%). Credit: ©Science China Press

Dilute magnetic semiconductors (DMS) have recently been a major focus of magnetic semiconductor research. A laboratory from the University of Science and Technology of China explored the feasibility of doping manganese (Mn) into zinc sulfide (ZnS) to obtain magnetic semiconductors.

Hideo Ohno and his group at the Tohoku University, Japan, were the first to measure [ferromagnetism](#) in transition metal-doped semiconductors such as [indium arsenide](#) and [gallium arsenide](#) doped with Mn. Ever since, researchers have attempted to obtain semiconductor hosts doped with different [transition metals](#) that exhibit ferromagnetic properties.

A team of researchers from Hefei National Laboratory for Physical Sciences at the Microscale, University of Science and Technology of

China, discovered that Mn-doped ZnS (ZnS:Mn) shows paramagnetic behavior and is not suitable for use as a DMS. Their work entitled "Structure Characterization, Magnetic and [Photoluminescence](#) Properties of Mn-Doped ZnS [Nanocrystalline](#)" was published in *SCIENCE CHINA Physics, Mechanics & Astronomy*, 2012, Vol 55(2) .

Electron spin resonance (ESR) spectra (Figure 1a) of nanocrystalline ZnS:Mn show that at lower concentrations of Mn, a typical sextet centered at a g-value of 2 is associated with the allowed ($\Delta m_s = \pm 1$, $\Delta m_l = 0$) magnetic dipole transitions between the hyperfine-split Zeeman levels of the $6S_{5/2}$ ground state of the Mn^{2+} 3d electrons. The hyperfine structure arises from the interaction between the $S=5/2$ spin of the unpaired 3d electrons with $I=5/2$ spin of the ^{55}Mn nucleus. This indicates that Mn ions are distributed in the ZnS nanocrystalline lattice so that they are isolated from each other. At higher concentrations of Mn, the ions assemble together and are localized in the ZnS crystal lattice, decreasing the Mn-Mn atomic distance and increasing the dipole-dipole interaction. This causes the hyperfine structure to merge into one broad resonance. Further ESR experiments (Figure 1b) at low temperature also suggested that the sample was not ferromagnetic. All of the results indicated that ZnS:Mn is paramagnetic and not suitable for DMS.

More information: Zuo M, Tan S, Li G P, et al. Structure characterization, magnetic and photoluminescence properties of Mn doped ZnS nanocrystalline. *SCIENCE CHINA Physics, Mechanics & Astronomy*, 2012, 55: 219-223

Provided by Science in China Press

Citation: Mn-doped ZnS is unsuitable to act as a dilute magnetic semiconductor (2012, February

20) retrieved 20 September 2024 from <https://phys.org/news/2012-02-mn-doped-zns-unsuitable-dilute-magnetic.html>

This document is subject to copyright. Apart from any fair dealing for the purpose of private study or research, no part may be reproduced without the written permission. The content is provided for information purposes only.